

ULTRA-GUARD 5700 ACCELERATOR CURATIVE

ULTRA-GUARD 5700 ACCELERATOR is a single component curative for Ultra-Guard 5700 High Solids Silicone Coating. Ultra-Guard 5700 Accelerator enhances the moisture curing characteristics and reduces the final cure time by 50%*.

Ultra-Guard 5700 Accelerator can be added and mixed into Ultra-Guard 5700 HS liquid coating at a rate of 1⁄4 pint per 5 gallon pail or 1 quart to 50 gallon drum.

RECOMMENDED USES

• Ultra-Guard 5700

PACKAGING

¼-pint can 1-quart can

COLOR

Light Yellow

TECHNICAL DATA

PHYSICAL PROPERTIES	
Form	Liquid
Odor	Hydrocarbon like
Density	8.4 lbs/gal
Boiling Point/Range	392°F (200°C)
Flash Point	266°F (130°C)
Water Solubility	Insoluble
Viscosity	200 cps
*Dry Time w/Accelerator 75 F, 50% RH	> 1 to 2 hours
Recoat Time	7 to 10 days between coats
Final Cure	30 days
*Actual cure time is dependent on weather o	conditions and application rate.

REQUIREMENTS

Ultra-Guard 5700 Accelerator should only be applied by professional applicators. Consult General Coatings Manufacturing Corp. for specific application requirements and end uses.

EQUIPMENT

For mixing 50 gallon drums we recommend a drum mixer of at least 2 ½ horsepower with a minimum of two 8 inch blades.

MIXING

Add accelerator to Ultra-Guard 5700. Using an air powered mixer capable of uniformly mixing the entire container, thoroughly mix accelerator into Ultra-Guard 5700.

Ultra-Guard 5700 is packaged with nitrogen to keep latent moisture from prematurely starting the curing process. After opening and catalyzing the Ultra-Guard 5700 is becomes much more sensitive to moisture and the entire container must be used in a relatively short period of time.

Equipment should be cleaned with an environmentally safe solvent, as permitted under local regulations, immediately after use.

PERSONAL PROTECTIVE EQUIPMENT

Since the coatings are atomized into a very fine particle distribution during spray application, it is essential that maximum effort is made to protect the spray mechanic and others near the workplace from undue exposure.

JOB-SITE PROTECTION

Overspray from Ultra-Guard Ultra-Guard 5700 Accelerator can carry considerable distances and attention should be given to the following:

- 1. Post warning signs a minimum of 100 feet from the work area.
- 2. Cover all intake vents near the work area.
- 3. Minimize or exclude all personnel not directly involved with the spray application.
- 4. No welding, smoking or open flames.
- 5. Have CO_2 or other dry chemical fire extinguisher available at the jobsite.
- 6. Provide adequate ventilation.

FREIGHT CLASSIFICATION

CORROSIVE LIQUID, N.O.S. (ORGANOTIN COMPOUND) Hazard Class: 8 Packing Group: III

SHELF LIFE AND STORAGE

Ultra-Guard 5700 Accelerator has a shelf life of one (1) year from date of manufacture in original, factory-sealed containers when stored indoors at a temperature between 60-95°F (15-35°C). Keep containers closed and store in a dry, cool place away from direct sunlight, heat, sparks, open flame, and moisture.

HEALTH & SAFETY

GCMC is committed to the health and safety of our customers. GCMC products shall only be installed by certified contractors. Applicators are required to follow all proper handling, safety and installation procedures. Any individual who may come in contact with these products should read and understand the SDS.

VAPOR INHALATION

The best form of protection against organic solvents or potentially sensitizing vapors in the workplace is a fresh air supply. Numerous manufacturers, including the 3M Company and MSA, make full face fresh air masks. For maximum protection, we recommend use of NIOSH/ MSHA approved self-contained breathing apparatus with a full-face piece operated in a positive pressure mode. In well-ventilated application conditions, the use of Type C organic vapor cartridge respirators is acceptable. Effects of overexposure to vapor are characterized by nasal and respiratory irritation, dizziness, nausea, headache, fatigue, possible unconsciousness or even asphyxiation. Vapor inhalation problems are characterized by coughing, shortening of breath and tightness in the chest. Anyone exhibiting these types of symptoms should be immediately removed from the workplace and administered oxygen or fresh air. If the condition is prolonged or extreme, SUMMON EMERGENCY TRAINED MEDICAL ATTENTION IMMEDIATELY.

SKIN CONTACT

To prevent excessive skin contact with the sprayed product, we recommend use of fabric coveralls and neoprene or other resistant gloves. Skin contact with liquid components can result in a rash or other irritation. Wash the affected skin area with water. Wipe residual liquid from the skin with a clean cloth, then wipe the affected area with 30% solution of rubbing alcohol. Follow the alcohol wipe with repeated washings with soap and water. If a rash or other irritation develops, see a physician.

EYE CONTACT

Wear a full-face mask or OSHA-approved protective goggles. Eye Contact with liquid or sprayed components can result in corneal burns or abrasions. Upon exposure, eyes should be flushed with water for an extensive period. SUMMON EMERGENCY TRAINED MEDICAL ATTENTION IMMEDIATELY.

FLAMMABILITY

Flash point is $142^{\circ}F$ (61°C). Avoid open flame or spark sources. Avoid excessive heat. Vapors are heavier than air and may travel along the ground or may be moved by ventilation and ignited by pilot lights, other flames, sparks, heaters, smoking, electric motors or other ignition sources at locations distant from the material-handling point. Never use a welding or cutting torch on or near the drum. In case of fire, use CO₂, steam, dry chemicals or water fog.

WARNING

This product contains Curatives.

TECHNICAL SERVICES

Additional information, such as brochures, technical assistance, roof energy evaluations, life cycle cost analysis, and other roof management services are also available from a General Coatings Manufacturing Corp. Technical Consultant.



ULTRA-GUARD 5700 ACCELERATOR CURATIVE

LIMITED WARRANTY. We warrant our Products to be free of manufacturing defects and to comply with the Product's current published physical properties when tested under controlled conditions. Our sole responsibility is limited to replacement of that portion of any Products found to be defective at the time of manufacture. There are no other warranties of any nature whatsoever, whether expressed or implied, including an express disclaimer of any warranty of merchantability or fitness for a particular purpose. Further, we disclaim any liability for damages of any type, however caused, including remote, consequential damages, or special damages resulting from any theory of liability, whether based on tort, negligence, or strict liability. We disclaim responsibility for any claims of intellectual property infringement through use of our Products in any manner. Where Products are used as a waterproofing membrane or floor coating, no warranty or guarantee is issued with respect to appearance, color, fading, chalking, staining, shrinkage, peeling, abnormal wear and tear, or improper application by the applicator. Damage caused by abuse, neglect, lack of proper maintenance, acts of nature and/or physical and performance analysis on any materials claimed to be defective, performed prior to any repairs being made by owner, general contractor, or applicator. Our limited warranty is void if repairs have been made or attempted, or if the claimed defect has been adulterated prior to our ability to conduct a formal investigative analysis.

DISCLAIMER: Please read all information in the general guidelines, technical data sheets, application guide and safety data sheets (SDS) before applying material. Products are for professional use only and should only be applied by professionals who have prior experience with our Products or have undergone specific training in their proper application. Published technical data and instructions are subject to change without notice. Contact your local representative or visit our website for current technical data and instructions. All guidelines, recommendations, statements, and technical data contained herein are based on information and tests we believe to be reliable and correct, but accuracy and completeness of these tests are not guaranteed and are not to be construed as a warranty, either expressed or implied, including any warranty of merchantability or fitness for a particular purpose in connection with any product. It is the user's responsibility to satisfy himself, by his own information and tests, to determine suitability of the product for his own intended use, application and job situation and user assumes all risk and liability resulting from his own use of the product. We do not suggest or guarantee that any hazards listed herein are the only ones that may exist. We are not liable to the purchaser, end-user, or any third party for any injury, loss or damage directly or indirectly resulting from use of, or inability to use, our Products. Recommendations or statements, whether verbal or in writing, shall not be binding upon us unless in writing and signed by one of our authorized corporate officers. Technical and application information is provided for establishing a general profile of the material and perior application proces. Test performance results were obtained in a controlled environment and we make no claim that these tests or any other tests, accurately represent all environments. We are not responsible for typographical errors. **@ General Coatings Manufacturing Corporation. All Rights Res**